

Basis	Adhesive for ebazell boards
Resin	Adhesive for ebazell
Hardener	Hardener adhesive ebazell
Colour	grey

Applications

- Bonding of ebazell - boards

Properties

- curing at room temperature
- very excellent filling- and flow properties
- very well workable

Processing data

Product		Mixture Adhesive for ebazell boards	Resin Adhesive for ebazell	Hardener Hardener adhesive ebazell
Colour		grey	grey	brown
Mixing ratio	p. b. w.		100	64
Viscosity at 25°C	mPas	thixotrop	thixotrop	200 ± 50
Density at 20°C	g / cm ³	0,80 ± 0,02	0,64 ± 0,02	1,22 ± 0,02
Pot life 100 g / 20°C	min.	15 - 20	-	-
Curing time at RT	hrs.	-	-	-

Sales units (packages)

Units	Adhesive	Adhesive for ebazell	0,500 kg
	Hardener	Hardener adhesive ebazell	0,320 kg

Processing instructions

Please stir material thoroughly before use. The adhesive is applied one-sided on adherend surface and is fixed by loading or slight tensioning.

Consumption: approx. 400 – 500 g/m²

The adhesive for **ebazell**-boards is applied with a 6-10 cm spatula.

In General

The adhesive is a two-component-system on Polyurethane base, which cures at room temperature. It consists of a filled base component and an isocyanate hardener (MDI).

The adhesive shows several advantages:

- same stability like **ebazell**-boards
- very easily dyeable
- low hardness
- low weight
- excellent filling properties

Storing

At room temperature (18 – 25°C) and closed original containers storage life is 9 months.

Partly used containers have to be closed always and the material has to be used up as soon as possible.

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

ebalta UK Limited . B2 Langham Park, Trent Lane . Castle Donington . Derbyshire DE74 2UT
t: +44 1332 814700 . f: +44 1332 814775 . e: info@**ebalta**.co.uk . w: www.**ebalta**.co.uk