

Basis	Putty for ebaboard L
Resin	Putty for ebaboard L
Hardener	Hardener for polyester
Colour	ochre

Applications

- Repairing for ebaboard L

Properties

- fine structure
- fast curing
- very well workable

Processing data

Product		Mixture Putty for ebaboard L	Resin Putty for ebaboard L	Hardener Hardener for polyester
Colour		ochre	ochre	white
Mixing ratio	p. b. w.		100	3
Viscosity at 25°C	mPas	Paste	thixotrop	thixotrop
Density at 20°C	g / cm ³	1,70 ± 0,03	-	1,15 ± 0,03
Pot life 200 g / 20°C	min.	4 - 6	-	-
Curing time at RT	min.	20 - 30	-	-

Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	-
Flexural modulus	EN ISO 178	MPa	-
Flexural strength at breakage	EN ISO 178	%	-
Flexural strength at breakage	ISO 37	%	-
Compressive strength	EN ISO 604	MPa	-
Impact resistance (Charpy)	EN ISO 179	kJ/m ²	-
Heat resistance (HDT)	DIN EN ISO 75 B	°C	-
Shore hardness	DIN 53505	Shore D	50 ± 2

Sales units (packages)

Units	Putty	Putty for ebaboard L	0,250 kg
	hardener	Hardener for polyester	0,060 kg

In General

The putty for **ebaboard L** is a two-components putty on polyester base. Therefore it's briefly polishable. It can be polished dry and wet. The abrasive dust doesn't contain any toxic substances, but should be exhausted for cleanup reasons. Excellent bonding on wood, plastic and metal. This putty for **ebaboard L** is easily and gently workable. It's also possible to draw in hollow flutes.

Storing

At room temperature (18 – 25°C) and closed original containers storage life is 6 months.
Partly used containers have always to be closed and the material has to be used up as soon as possible.

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

ebalta UK Limited . B2 Langham Park, Trent Lane . Castle Donington . Derbyshire DE74 2UT
t: +44 1332 814700 . f: +44 1332 814775 . e: info@**ebalta**.co.uk . w: www.**ebalta**.co.uk