

Typical Properties
TB400
Low Density Epoxy Tooling Block

Property	Test Method	Value	SI Units	Value	Imp Units
Colour	-	Beige		-	
Density	BS EN ISO 1183-3:1999	400	kg/m ³	25	lb/ft ³
Shore Hardness	ISO 868:1998	55	'D	55	°D
Flexural Strength	BS EN ISO 178	11,0	MPa	1,600	lb/in ²
Flexural Modulus	BS EN ISO 178	1,300	MPa	188,600	lb/in ²
Uniaxial Compressive Strength	BS EN ISO 604	11.0	MPa	1,600	lb/in ²
Heat Distortion Temperature	BS 2782	115	°C	239	°F
Glass Transition Temperature	BS ISO 11357-2	120	°C	248	°F
Coefficient of Thermal Expansion	BS 4618 3,1	20,0	x 'K ⁻¹ IT	11.1	x 10 ⁴ °F

Author	Dave Williams	Issue No	2
Approved By	Sim Chow	Date of Approval/issue	05 Mar 2008

The Information given within this document is of a general nature only. The values given must be considered as typical and do not constitute a product specification. No liability for loss or damage can be accepted by Trelleborg CRP Ltd. Unless otherwise stated, all properties are quoted at ambient conditions.

All information contained herein is the proprietary information of Trelleborg CRP Ltd and must not be copied or disclosed to any other party without the prior written permission of Trelleborg CRP Ltd. The information contained herein must only be used for the Specific Purpose for which it was provided.