

Basis	Flexible PU casting resin
Resin	GM 951 Thix Comp. A
Hardener	GM 951 Comp. B
Colour	black

Applications

- Sealing profiles in core boxes
- Casting mould for gypsum
- Casting mould for plastic
- Casting mould for wax
- Casting mould for ceramic materials
- Casting mould for PU-foam
- Casting mould for cement
- Gaskets
- Jigs

Properties

- spreadable
- shore A hardness about 50
- high tear strength

Processing data

Product		Mixture GM 951 Thix / Comp. A+B	Resin GM 951 Thix Comp. A	Hardener GM 951 Comp. B
Colour		black	black	transparent
Mixing ratio	p. b. w.		100	10
Viscosity at 25°C	mPas	thixotrop	thixotrop	-
Density at 20°C	g / cm ³	1,20 ± 0,03	1,04 ± 0,02	0,962 ± 0,03
Pot life 200 g / 20°C	min.	25 - 30	-	-
Curing time at RT	hrs.	2 - 5	-	-

Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	-
Flexural modulus	EN ISO 178	MPa	-
Flexural strength at breakage	EN ISO 178	%	-
Tensile strength	EN ISO 527	MPa	2,0 ± 0,5
Elongation	EN ISO 527	%	600 ± 50
Compressive strength	EN ISO 604	MPa	-
Impact resistance (Charpy)	EN ISO 179	kJ/m ²	-
Heat resistance (Martens)	DIN 53458	°C	-
TG in TMA T _g	Methode TMA	°C	-
Shore hardness	DIN 53505	Shore A	55 ± 5
Coefficient of linear expansion	DIN 53752	10 ⁻⁶ K ⁻¹	-
Linear shrinkage	internal	%	-
Tear resistance / angle test piece	EN ISO 34-1	kN/m	10 ± 05

Sales units (packages)

Packing size A - Pack GM 951 Thix / Comp. A+B Resin 12 x 0,300 kg /Hardener 12 x 0,030 kg = 3,960 kg

Processing instructions

Material- and working- temperature: between 18 - 25 °C.

Close containers after use.

Seal porous mould surfaces first (**ebalta** mould sealer).

For optimum mould releasing we recommend a special release agent (like T1-1), which can be applied easily with a brush or be sprayed. Releasing of the mould 2-3 times, evaporate for about 20 min. after each releasing.

Mixing ratio resin/hardener according to instructions.

Stirring rods etc. with residual resin can be easily cleaned with **ebalta** cleaning agent

Both components can be easily mixed free from air bubbles in small quantities by hand with a round stirring rod or in larger quantities with a spiral stirrer.

In General

ebalta GM 951 Thix is a brushable gel coat suitable as a flexible casting system.

Mould temperatures of about 60 °C enable fast curing and therefore shorter demoulding time.

Storing

Storage at room temperature 18-25 °C.

Already opened containers should be closed immediately after use and should be used as soon as possible.

Information about the expiration date you find on the sales packages.

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices!

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

ebalta UK Limited . B2 Langham Park, Trent Lane . Castle Donington . Derbyshire DE74 2UT
t: +44 1332 814700 . f: +44 1332 814775 . e: info@**ebalta**.co.uk . w: www.**ebalta**.co.uk