

Basis	very abrasion resistant gel coat
Resin	OH 6-1
Hardener	CH-1
Colour	blue

Applications

- Foundry patterns
- Coping models
- Polyester hand lay-up moulds
- PU-foaming tools

Properties

- fine structure
- very abrasion resistant
- very hard

Processing data

Product		Mixture OH 6-1 / CH-1	Resin OH 6-1	Hardener CH-1
Colour		blue	blue	yellow transparent
Mixing ratio	p. b. w.		100	11
Viscosity at 25°C	mPas	thixotrop	pasty	3500 ± 500
Density at 20°C	g / cm ³	1,75 ± 0,05	1,83 ± 0,05	1,08 ± 0,02
Pot life 200 g / 20°C	min.	20 - 25	-	-
Curing time at RT	hrs.	20 - 24	-	-
Post curing	Time in h/ Temperature in °C	-	-	-

Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	90 ± 5
Flexural strength at breakage	EN ISO 178	%	1,7 ± 0,2
Flexural modulus	EN ISO 178	MPa	7500 ± 700
Tensile strength	EN ISO 527	MPa	-
Tensile strength / test piece type 2	ISO 37	MPa	-
Elongation at break	ISO 37	%	-
Impact resistance (Charpy)	EN ISO 179	kJ/m ²	9 ± 1
Compressive strength	EN ISO 604	MPa	115 ± 10
Heat resistance (HDT)	DIN EN ISO 75 B	°C	98 ± 3
Glass transition temperature TG	methode DSC	°C	-
Shore hardness	DIN 53505	Shore D	90 ± 3
Coefficient of linear expansion	DIN 53752	10 ⁻⁶ K ⁻¹	ca. 51
Abrasion Taber Abraser H 18 Application weight 500g / 250 Rotations	internal	mg	ca. 71

Sales units (packages)

Packing size	A-Pack	OH 6-1 / CH-1	resin 12 x 0,500 kg + hardener 12 x 0,055 kg = 6,660 kg
Units	Resin	OH 6-1	6,000 kg
	Hardener	CH-1	1,000 kg / 5,000 kg

Processing instructions

The temperature of material and processing should be between 18 and 25° C.

After each use the containers have to be closed again.

Porous mould surfaces should be sealed before (**ebalta** sealant).

For an optimum mould release we recommend a suitable release agent (e.g. T 1-1) which can be easily applied with a brush.

The mould should be treated 2 or 3 times with release agent and allowed to evaporate for approx. 20 min after every application.

Mixing ratio resin/hardener according to instructions!

Stirring rods etc. with residual resin can be easily cleaned with **ebalta** cleaning agent.

Storing

Storage at room temperature 18-25 °C.

Opened containers should be closed immediately after use and should be used up as soon as possible.

Shelf life is indicated on the labels.

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

ebalta UK Limited . B2 Langham Park, Trent Lane . Castle Donington . Derbyshire DE74 2UT
t: +44 1332 814700 . f: +44 1332 814775 . e: info@**ebalta**.co.uk . w: www.**ebalta**.co.uk