

(Also known in Europe as OH6-1 / SR)

Basis	Very abrasion resistant gelcoat
Resin	OH 6
Hardener	SR
Colour	blue
Further colours	yellow, red, grey, green
Further hardeners	CH-1

Applications

- Foundry patterns
- PU-foaming tools
- Polyester hand lay-up mould
- Coping models

Properties

- very abrasion resistant
- very hard
- fine structure

Processing data

Product		Mixture OH 6 / SR	Resin OH 6	Hardener SR
Colour		blue	blue	amber
Mixing ratio	p. b. w.		100	9
Viscosity at 25°C	mPas	thixotrope	pasty	1650 ± 50
Density at 20°C	g / cm ³	1,75 ± 0,05	1,83 ± 0,05	1,07 ± 0,02
Pot life 200 g / 20°C	min.	15 - 20	-	-
Curing time at RT	hrs.	5 - 8	-	-
Post curing	Time in h/ Temperature in °C	-	-	-

Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	105 ± 8
Flexural modulus	EN ISO 178	MPa	6650 ± 400
Flexural strength at breakage	EN ISO 178	%	2,05 ± 0,2
Tensile strength	EN ISO 527	MPa	-
Compressive strength	EN ISO 604	MPa	104 ± 8
Impact resistance (Charpy)	EN ISO 179	kJ/m ²	-
Heat resistance (HDT)	DIN EN ISO 75 B	°C	94 ± 3
Shore hardness	DIN 53505	Shore D	85 ± 3
Coefficient of linear expansion	DIN 53752	10 ⁻⁶ K ⁻¹	ca. 42
Abrasion Taber Abraser H 18 Application weight 500g / 250 Rotations	internal	mg	ca. 36

Sales units (packages)

Packing size	A - Pack	OH 6 / SR	Resin 12 x 0,500 kg + Hardener 12 x 0,045 kg = 6,540 kg
Units	Resin	OH 6	6,000 kg
	Hardener		1,000 kg / 5,000 kg / 50,000 kg

Processing instructions

The temperature of material and processing should be between 18 and 25° C.

After each use the containers have to be closed again.

Porous mould surfaces should be sealed before (**ebalta** sealant).

For an optimum mould release we recommend a suitable release agent (e.g. T 1-1) which can be easily applied with a brush. The mould should be treated 2 or 3 times with release agent and allowed to evaporate for approx. 20 min after every application.

Mixing ratio resin/hardener according to instructions!

Stirring rods etc. with residual resin can be easily cleaned with **ebalta** cleaning agent.

In General

ebalta OH 6/SR is an abrasion resistant epoxy gelcoat, curing at room temperature with almost no shrinkage. Due to its fine granular and extremely hard fillers it shows excellent demoulding properties and a very good wear resistance.

The resin/hardener mixture can be applied with a short-haired brush in a 1 mm layer, no sagging at edges, corners and vertical surfaces.

With CH hardener OH 6 is resistant to many chemicals and solvents. For this reason we recommend OH 6/CH also for PU-foam mouldings as well as for polyesterhand lay-up mouldings.

Storing

Storage at room temperature (18-25 °C) in closed original container 6 months.

Already opened containers should be closed immediately after use and should be used as soon as possible

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

ebalta UK Limited . B2 Langham Park, Trent Lane . Castle Donington . Derbyshire DE74 2UT
t: +44 1332 814700 . f: +44 1332 814775 . e: info@**ebalta**.co.uk . w: www.**ebalta**.co.uk