

Basis	Supple, temperature resistant laminating paste
Resin	PS 05
Hardener	TLB
Colour	grey

### Applications

- Vacuum forming tools
- PU-foaming tools
- Polyester press forms
- Prepreg tool
- Adhesive probes

### Properties

- low shrinkage
- soft
- heat resistant

### Processing data

Product		Mixture PS 05/ TLB	Resin PS 05	Hardener TLB
Colour		grey	grey	blue
<b>Mixing ratio</b>	<b>p. b. w.</b>		<b>100</b>	<b>13</b>
Viscosity at 25°C	mPas	pasty	pasty	300 ± 100
Density at 20°C	g / cm <sup>3</sup>	1,10 ± 0,05	1,10 ± 0,05	0,98 ± 0,02
Pot life 200 g / 20°C	min.	50 - 60	-	-
Curing time at RT	hrs.	16 - 24	-	-

### Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	47 ± 5
Flexural modulus	EN ISO 178	MPa	4985 ± 700
Flexural strength at breakage	EN ISO 178	%	1,0 ± 0,2
Compressive strength	EN ISO 604	MPa	75 ± 5
Impact resistance (Charpy)	EN ISO 179	kJ/m <sup>2</sup>	4,6 ± 0,7
Heat resistance (HDT)	DIN EN ISO 75 B	°C	105 ± 5
Shore hardness	DIN 53505	Shore D	80 ± 3
Coefficient of linear expansion	DIN 53752	10 <sup>-6</sup> K <sup>-1</sup>	ca. 32

### Sales units (packages)

Units	Resin	PS 05	20,000 kg
	Hardener	TLB	2,600 kg / 5,000 kg

## Processing instructions

The mixing of the smooth resin paste with the liquid hardener should be executed in a mechanical mixer. Please note that always small quantities should be prepared (max. 10 kg) , so that an excellent mixing is possible. But **ebalta** PS 05/TLB can also be mixed with a star stirrer in a hand drill gun or small quantities by hand. A good mixing can be made out when a uniform colour shade is built from the blue hardener and the grey resin paste. The laminate system tends to build up high reaction temperatures at temperatures higher than 25°C. This develops tensions, which could lead to distortion of the tool.

## In General

**ebalta** PS 05/TLB is a very smooth, glass fiber filled two-component-epoxy resin paste, which cures at room temperature with a thickness of 15 - 20 mm without considerable shrinkage and which is temperature resistant after a single post-curing of approx. 10 hours at 60-80°C to 90°C.

This laminate paste is a system, which consists of glass fiber and reinforcing material. Due to the coloured hardener the mixing of paste and hardener can be easily controlled.

The mixture can be applied without problems and shows a excellent strength after curing.

The mixed laminate paste has a low specific weight and is therefore very suitable for the lightweight construction of large-area reinforcements.

## Storing

At appropriate storage (room temperature) in closed original container 12 months. Occuring crystallization due to unfavourable storage conditions can be neutralized by warming up the material at approx. 60° C.

Already opened containers should be closed immediately after use and be protected against moisture. This material should be used as soon as possible.

## Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

## Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

**ebalta** UK Limited . B2 Langham Park, Trent Lane . Castle Donington . Derbyshire DE74 2UT  
t: +44 1332 814700 . f: +44 1332 814775 . e: info@**ebalta**.co.uk . w: www.**ebalta**.co.uk