

Basis	Temperature resistant tooling paste
Resin	PS 06
Hardener	TL
Colour	alu grey

### Applications

- Foam tools
- Polyester press tool
- Vacuum forming tools

### Properties

- heat resistant
- good conductivity
- good compressive strength
- glassfibre filled
- aluminium filled

### Processing data

Product		Mixture PS 06 / TL	Resin PS 06	Hardener TL
Colour		alu grey	alu grey	yellow transparent
<b>Mixing ratio</b>	<b>p. b. w.</b>		<b>100</b>	<b>4</b>
Viscosity at 25°C	mPas	pasty	pasty	200 ± 50
Density at 20°C	g / cm <sup>3</sup>	1,90 ± 0,05	1,90 ± 0,05	0,967 ± 0,010
Pot life 200 g / 20°C	min.	50 - 60	-	-
Curing time at RT	hrs.	12 - 18	-	-
Post curing	Time in h/ Temperature in °C	-	-	-

### Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	52 ± 5
Flexural modulus	EN ISO 178	MPa	4850 ± 500
Flexural strength at breakage	EN ISO 178	%	1,8 ± 0,2
Compressive strength	EN ISO 604	MPa	105 ± 10
Impact resistance (Charpy)	EN ISO 179	kJ/m <sup>2</sup>	4,2 ± 0,5
Heat resistance (Martens)	DIN 53458	°C	104 ± 3
Shore hardness	DIN 53505	Shore D	87 ± 2
Coefficient of linear expansion	DIN 53752	10 <sup>-6</sup> K <sup>-1</sup>	-

### Sales units (packages)

Units	Resin	PS 06	25,000 kg
	Hardener	TL	1,000 kg / 5,000 kg

## Processing instructions

The mixing of the glass fiber and aluminium particle filled reinforcing paste PS 06 with the hardener TL should be made in a mechanical kneader. Smaller quantities can also be mixed with a spiral stirrer in a hand drilling gun or by hand.

The mixed paste should be applied directly on the fresh surface layer or on the coupling layer KP 6/TGL and should be well compressed.

Heating and cooling coils can be inserted into the paste

## In General

**ebalta** PS 06/TL is an aluminium- and glass fiber consisting, temperature-resistant two-component-epoxy paste, which cures at room temperature. After the curing a compact system is built, which is resistant to compression. Furthermore the system shows a good heat conductivity.

Ebalta PS 06/TL can be applied in one step in the thickness 30-40 mm. After a single post-curing at 50-60°C for 10-12 hours the reinforcing paste is temperature resistant up to 110°C.

## Storing

At appropriate storage (room temperature) in closed original container 12 months. Occuring crystallization due to unfavourable storage conditions can be neutralized by warming up the material at approx. 60° C.

Already opened containers should be closed immediately after use and be protected against moisture. This material should be used as soon as possible.

## Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

## Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

**ebalta** UK Limited . B2 Langham Park, Trent Lane . Castle Donington . Derbyshire DE74 2UT  
t: +44 1332 814700 . f: +44 1332 814775 . e: info@**ebalta**.co.uk . w: www.**ebalta**.co.uk